

FEATURES OF YCC RUBBER MATERIAL FOR PNEUMATIC SEAL AND PACKINGS

MATERIAL CHARACTERISTICS	YCC CODE	NBR	NBR	NBR	NBR
NORMAL CONDITION	HARDNESS (JIS Hs)	75 ± 5	80 ± 5	85 ± 5	90 ± 5
	TENSILE STRENGTH MIN.	160	165	165	170
	ELONGATION(%) MIN.	250	200	200	150
COMPRESSION SET OF STANDARD TEST SPECIMEN	°C / Hrs.	100°C/70	100°C/70	100°C/70	100°C/70
	(%)MAX	20	20	20	25
FEATURES		APPLICABLE FOR OILING, OILLESS, DRY AIR CONDITION			
RECOMMENDED YCC TYPES		APA、APP、 GLY、APN、 RP、ANSP、 APG、PRY	AGP、ARY	AVB	AEI

